

**Europäisches
Patentamt****European
Patent Office****Office européen
des brevets**

REC'D 15 OCT 2003

WIBO PCT

Bescheinigung**Certificate****Attestation**

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

02079250.3

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

R C van Dijk**Best Available Copy**



Anmeldung Nr:
Application no.: 02079250.3
Demande no:

Anmeldetag:
Date of filing: 11.10.02
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Koninklijke Philips Electronics N.V.
Groenewoudseweg 1
5621 BA Eindhoven
PAYS-BAS

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se referer à la description.)

Light-transmitting substrate provided with a light-absorbong coating

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

H01K/

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SK TR

Light-transmitting substrate provided with a light-absorbing coating

The present invention relates to a light-transmitting substrate that is at least partly provided with a light-absorbing coating, said coating comprising silver and/or gold particles that are incorporated in a sol-gel matrix. The invention further relates to an electric lamp comprising a light-transmitting lamp vessel that accommodates a light source, wherein
5 said lamp vessel comprises the above light-transmitting substrate. Furthermore the present invention relates to the light absorbing coating itself.

Light-transmitting substrates provided with a light absorbing coating can be used as a color layer on or in front of (incandescent) lamps for general lighting purposes. The substrate may comprise, for example, a colored filter made of a - flat or non-flat shaped -
10 piece of glass, which is designated to be placed on trajectory of light, said light being generated by a lamp. Such application is often used in outdoor lighting. Another example of a light-transmitting substrate is a lamp vessel that is placed over a light source of an electric lamp. Such electric lamps are predominantly used as indicator lamps in vehicles, for example as red-colored light source in red tail and brake lights of automobiles. Said electric lamps can
15 also be used in traffic lights.

The main advantage of using specifically metal particles such as silver or gold, over ordinary - organic or inorganic - pigments is the absence of thermochromic behavior. In addition diffuse scattering is very small due to the extremely small size of the particles.

The color appearance of a coating material containing metal nanoparticles, such as gold and silver, can be tuned as the optical absorption of metal particles is shifted
20 towards longer wavelengths when they are embedded in dielectrics with higher refractive indices. For example, for gold particles the absorption peak shifts from 520 nm (green) to 620 nm (red) when incorporated in a SiO₂-matrix or a TiO₂ matrix, respectively. Choosing the proper metal and matrix material can obtain a specific color.

25 A coating comprising silver or gold incorporated in a sol-gel matrix is known, for example, from US-A-5,731,091.

However, an important disadvantage of said coatings is that the gold and silver particles embedded in a suitable matrix material are strongly absorbing in the yellow-green part of the spectrum in particular. This results in coatings that are transmitting in the blue and

red part of the spectrum. In order to reduce the blue transmission sufficiently and to obtain red transmitting coatings, large amounts of gold and silver particles are needed. It will be clear that this is a cost disadvantage. In addition, by decreasing the blue transmission of the coating, also the red absorption is decreased, thus decreasing the effective light output of the lamp. In case of coatings comprising silver, the main drawback is the small transmittance of a red coating, which is less than about 11%.

The present invention aims to provide for a light-transmitting substrate according to the preamble, in which the above mentioned disadvantages are obviated. Moreover, the present invention aims to provide for a coating that does not show the above mentioned disadvantages.

To this end, the present invention provides for a light-transmitting substrate according to the preamble that is characterized in that a blue absorbing compound is added to the coating.

By adding a blue absorbing compound to the coating, such that the light in the blue part of the spectrum is absorbed, a red transmitting coating is obtained without the need for very high amounts of gold or silver particles. On the contrary, the amounts of gold and silver can be reduced considerably. For example, in the case of gold, the amount can be reduced by a factor of 5. In the case of silver, an additional advantage is that a matrix with a higher refractive index can be used, for example about 2.3, causing the transmittance to rise to 20%.

Such blue absorbing compound absorbs the light in the blue part of the spectrum. Thus, in case of a light-absorbing coating comprising silver and/or gold particles, that is strongly absorbing in the yellow-green part of the spectrum, the addition of a blue absorbing compound results in absorption in both the yellow-green and the blue part of the spectrum. Hereby the red part of the spectrum remains light transmitting, without the need for very high amounts of silver or gold particles.

The blue absorbing compound may either be an organic or an inorganic compound. In general each yellow absorbing pigment can be used as long as the absorption at wavelengths above 590 nm is very low or negligible. The temperature to which the substrate – for example the glass vessel – is subjected also determines the choice between organic or inorganic compound. In case of high temperatures inorganic compounds are preferred, while in case of lower temperatures organic compounds can be advantageous.

The blue absorbing compound can be added to the light-absorbing coating layer. However, in a particular embodiment, the blue absorbing compound is present in an additional layer.

Such additional layer is preferably adjacent to the light-absorbing coating layer. The additional layer may be applied on top of the coating or between the coating and the substrate.

However, in another preferred embodiment of the present invention, the blue absorbing compound is present in the substrate. For example, the blue absorbing compound may be present in the glass of the lamp vessel.

Preferred examples for the inorganic compounds comprise Fe_2O_3 , compounds with the general formula $\text{Zn}_{(1-x)}\text{Fe}_{(2+x)}\text{O}_4$, such as $\text{Zn Fe}_2\text{O}_4$ or V_2O_5 . However, other inorganic compounds may also provide for good results. For example, Ag may be added to an Au/MTMS coating in order to provide for absorption in blue.

The above-mentioned blue absorbing compounds or pigments are very well known. For example, Fe_2O_3 is as such also used as the main pigment in a light-absorbing coating for a lamp vessel of an electric lamp. Iron oxide (Fe_2O_3) is an orange pigment and P-doped Fe_2O_3 is an orange-red pigment. To this end reference is made to WO 01/20641 in the name of the Applicant. An important difference between WO 01/20641 and the present invention is that in WO 01/20641 the inorganic pigment is used as the main pigment for absorbing part of the visible light, while in the present invention, gold and silver are the main light absorbing constituents. In the present invention, the inorganic pigment is specifically added to absorb the light in the blue region thereby allowing for lesser amounts of gold and silver.

The present invention also relates to an electric lamp comprising a light-transmitting lamp vessel which accommodates a light source, said lamp vessel comprising a light-transmitting substrate according to the above.

As mentioned in the above, said electric lamps can advantageously be used as indicator lamps in vehicles, for example as red-colored light source in red tail and brake lights of automobiles.

Moreover, the present invention relates to a light absorbing coating according to the above.

These and other aspects of the invention will be apparent from and elucidated with reference to the embodiments described hereinafter.

In the drawings:

Fig. 1 shows, in a part of a C.I.E. chromaticity diagram, the color co-ordinates of a light transmitting substrate provided with a light absorbing coating containing gold particles;

Fig. 2 shows, in a part of a C.I.E. chromaticity diagram, the color co-ordinates of a light transmitting substrate provided with a light absorbing coating containing silver particles.

The present invention will be elucidated by means of the following manufacturing examples of preparing a coating and applying said coating to a substrate.

Example 1 - Gold in MTMS/TEOS

A sol-gel hydrolysis mixture is made by mixing 4.3 g ethanol, 40.0 g methyltrimethoxy silane (MTMS), 0.86 g tetraethoxy silane (TEOS) and 0.14 g 0.1 M Acetic acid in 32.0 g water and subjecting said mixture to hydrolysis during 48 hours.

A Fe_2O_3 dispersion is made by mixing 3 g Fe_2O_3 , 3 g Dysperbyk-190, 7 g water and 10 g ethanol. This dispersion is added to the sol-gel hydrolysis mixture and methoxypropanol in a 1:2:0.2 ratio. Spin coating of the resulting solution on a glass plate or spraying onto a rotating glass envelop results in a 2 μm thick coating containing about 20 vol.-% Fe_2O_3 .

Subsequently, 1 g of a Au particle dispersion comprising 25 wt% gold particles, 7 wt% polymer and 68 wt% is mixed with a sol-gel hydrolysis mixture similar to the one described above in a 1-to-2 ratio. The polymer that is used to stabilize the metal particles is a polystyrene-polycarbonate blockcopolymer.

The coating liquid is subsequently spin coated onto the outer surface of a glass substrate covered with the Fe_2O_3 containing coating. The coating is cured for 30 minutes at a temperature of 350°C resulting in a red coating. The layer thickness is about 2.8 μm .

A similar result can be obtained when the Au-dispersion is directly added to the mixture containing the sol-gel hydrolysis mixture and the Fe_2O_3 containing dispersion. The layer is then applied in a single step.

Example 2 – Silver in TEOTi

First a 2 μm thick silica layer containing about 20 vol.% Fe_2O_3 is applied as in example 1.

5 A sol-gel hydrolysis mixture is made by mixing 20 g ethanol, 3.3 g tetraethoxy titane (TEOTi), and 2.35 g 0.1 M HCl and subjecting said mixture to hydrolysis during 48 hours.

Subsequently, a 1 g of a Ag particle dispersion comprising 17 wt% silver particles, 13 wt% polymer and 70 wt% ethanol, is added to 2 g of ethanol and 2.5 g of 10wt-% N-aminopropyltrimethoxysilane in ethanol. This solution is mixed with the TEOTi
10 solution in a ratio of 1-to-2.. The polymer that is used to stabilize the metal particles is a polystyrene-polycarbonate blockcopolymer.

The coating liquid is prepared by mixing the silver solution and the sol-gel hydrolysis mixture. The coating liquid is subsequently spin coated onto a glass substrate covered with a Fe_2O_3 containing coating and cured at a temperature of 350°C in air. The
15 layer thickness of the coating is 200 nm.

Fig. 1 shows, in a part of a C.I.E. chromaticity diagram, the color co-ordinates of a light transmitting substrate provided with a light absorbing coating comprising Au particles as obtained from simulations. The red color is specified by $x=0.665$ and $y=0.335$.

In the left side of figure 1 the color point is shown of a 2 μm thick coatings of
20 gold particles incorporated in a matrix. The refractive index varies from 1.46 up to 1.90 and the Au content varies from 0.5 up to 3 vol.%. Only at the 3 vol.% Au content the transmitted color falls within the red specification. The highest transmission is then obtained with a refractive index of about 1.5. The layers containing a smaller amount of Au fail to produce a red color because their transmission in the blue region is too large.

25 In the right side of figure 1 is shown how the addition of Fe_2O_3 to the light absorbing coating improves the red color transmission. By using the coating according to the present invention – e.g. the coating according to example 1: a Au/sol-gel coating to which about 20 vol.% Fe_2O_3 is added – the blue transmission is effectively blocked. In this way a layer with a refractive index of 1.90 containing only 0.5 vol.% Au comes within the red
30 specification. When the index of the layer is small ($n=1.5$), the amount of Au can be lowered to about 2 vol.%.

Fig. 2 shows, in a part of a C.I.E. chromaticity diagram, the color co-ordinates of a light transmitting substrate provided with a light absorbing coating containing silver particles as obtained from simulations.

PHNL021043EPP

6

11.10.2002

It is clearly shown that the coating that does not contain any Fe_2O_3 or any Fe_2O_3 layer adjacent to it, fails to produce a red color according to the specification.

However, the addition of a 2 μm thick silica layer containing about 20 vol. %

Fe_2O_3 to the Ag containing coating layer - e.g. according to example 2 - shifts the color

5 point toward the red region. As shown in figure 2, the color point and transmission are not strongly dependent on the position of the Fe_2O_3 layer.

It will be clear that, within the scope of the invention, many variations are possible to those skilled in the art. Many alternative preparation methods, both wet-chemical and by using physical-deposition methods are possible. Furthermore, it is also possible to use

10 other blue absorbing compound combinations to cause the desired color point shift.

The scope of protection of the invention is not limited to the examples given herein. The invention is embodied in each novel characteristic and each combination of characteristics.

CLAIMS:

1. A light-transmitting substrate which is at least partly provided with a light-absorbing coating, said coating comprising silver and/or gold particles that are incorporated in a sol-gel matrix, a blue absorbing compound being added to the coating.

5 2. A light-transmitting substrate according to claim 1, characterized in that the blue absorbing compound is present in an additional layer.

3. A light-transmitting substrate according to claim 1, characterized in that the blue absorbing compound is present in the substrate.

10

4. A light-transmitting substrate according to claim 1, characterized in that the blue-absorbing compound comprises an inorganic compound.

15 5. A light-transmitting substrate according to claim 4, characterized in that the inorganic compound comprises Fe_2O_3 , compounds with the general formula $\text{Zn}_{(1-x)}\text{Fe}_{(2+x)}\text{O}_4$, such as $\text{Zn Fe}_2\text{O}_4$, or V_2O_5 .

20 6. An electric lamp comprising a light-transmitting lamp vessel that accommodates a light source, said lamp vessel comprising a light-transmitting substrate according to one or more of claims 1-5.

7. Light absorbing coating according to one or more of claims 1-5.

PHNLO21043EPP

8

11.10.2002

ABSTRACT:

Disclosed is a light-transmitting substrate that is at least partly provided with a light-absorbing coating. Said coating comprises silver or gold particles that are incorporated in a sol-gel matrix. In order to improve the transmittance in red and to reduce the amount of silver and gold particles, a blue absorbing compound is added to the coating.

5 Further an electric lamp is disclosed, said lamp comprising a light-transmitting lamp vessel that accommodates a light source. Said lamp vessel comprises the above light-transmitting substrate. Moreover, a light-absorbing coating is disclosed.

Fig. 1

1/2




FIG.1

2/2




FIG.2

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☒ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☒ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☒ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.